



www.mondialcolor.it



COMPANY WITH  
CERTIFIED MANAGEMENT SYSTEM  
= UNI EN ISO 9001 =

## PRODUCT DATA SHEET

**PRODUCT:** **MONDIALMAX SL**  
**Synthetic fast drying finish - semi-gloss**

**CODE:** **COMP. A 221**  
**COMP. B -**

**PRODUCT DESCRIPTION:** Fast drying enamel for general use, plant engineering, carpentry and metal structures in general. Excellent aging stability, minimal tonal variations, great resistance to chalking. Suitable for use in outdoor, marine and industrial environments moderately aggressive. Excellent adhesion and flexibility, even directly on metal. Not applicable directly on aluminum, hot dip galvanized steel and inorganic zinc.

**SURFACE PREPARATION:** The product is applied on surfaces already primed, rigorously dry, clean, perfectly free of oil, grease, dust, moisture or other contaminants.

**APPLICATION METHODS:** Spray, brush or roll. Preferred application is airless spray. Brush or roller don't grant a uniform coverage, use these techniques only on retouch or small surfaces. For small and non-continuous surfaces, we suggest use of manual spray gun or airmix pumps.

<b>APPLICATION INSTRUCTIONS:</b>	<b>CONVENTIONAL SPRAY LOW PRESSURE PUMP</b>		<b>AIRLESS AIRMIX</b>	
	Nozzle diameter (mm)	<b>1,8÷2,0</b>	Pressure ratio	<b>28:1</b>
Product pressure (Atm)	<b>1,0÷1,7</b>	Nozzle diameter (inch)	<b>0,015÷0,019</b>	
Air pressure	<b>3,5÷5,0</b>	Product pressure (Atm)	<b>110,0÷150,0</b>	



www.mondialcolor.it



COMPANY WITH  
CERTIFIED MANAGEMENT SYSTEM  
= UNI EN ISO 9001 =

## TECHNICAL DATA:

	<b>Evaporation of the solvent and oxidation</b>
Mechanism of hardening	
Specific weight (kg / l) *	<b>1,3 (±5%)</b>
Volume solids (%) *	<b>50,4 (±1%)</b>
Medium dry film thickness (microns)	<b>40</b>
Correspondence wet film thickness (microns)	<b>82</b>
Yield to the average or recommended thickness (m <sup>2</sup> / kg) *	<b>9,7</b>
Yield to the average or recommended thickness (m <sup>2</sup> / lt) *	<b>12,6</b>
Consumption at the average or recommended thickness (Kg / m <sup>2</sup> ) *	<b>0,12</b>
Touch dry at 25 ° C (min)	<b>20</b>
Recoat time min. recommended 25 ° C (hours)	<b>12</b>
Recoat time max. recommended 25 ° C (days)	<b>-</b>
Hard dry at 25 ° C (days)	<b>2</b>
Maximum operating temperature (° C)	<b>98</b>
Recommended application temperature (° C)	<b>+5~ +35</b>
Thinner	<b>6000015 - 6000005</b>
Aspect of the film	<b>semigloss</b>
Color	<b>On request</b>
Storage in suitable conditions (months)	<b>12</b>

N.B.

\* Data referred to colour white. The solid content values, specific weight and yield were calculated with theoretical method. Thickness and performance are indicative, in fact vary greatly depending condition of substrate, absorption, porosity, surface irregularities and application method.



[www.mondialcolor.it](http://www.mondialcolor.it)



COMPANY WITH  
CERTIFIED MANAGEMENT SYSTEM  
= UNI EN ISO 9001 =

#### **ADDITIONAL INFORMATION:**

This is a one-component product. Vigorously mix the product for a few minutes with appropriate instruments and characterized by sufficient size, in order to ensure the complete homogeneity. Where possible it is preferable to use a mechanical stirrer. The temperature of the surface to be treated must be at least 3° C higher than dew point. If this condition is not met the resulting condensation, not always visible, may easily lead to phenomena of non-adherence. Carefully remove any accumulated roughness prior to the application of subsequent coats. It is recommended to implement all necessary measures (development of equipment for painting, using any thinner retardant-wetting thinner, position yourself upwind, proper progression of the surfaces to be painted) to prevent the accumulation of dust coating, which often causes inhomogeneity of the film.

---

#### **IMPORTANT NOTE**

All information contained in this form are the result of laboratory tests carried out under controlled conditions and well-defined and / or correspond to our most advanced and current technical and practical knowledge. this does not exempt the customer, given the variability of environmental conditions and personal systems of application, from carrying out their own investigations and to make their own eligibility checks. Mondial Color assumes no responsibility for any damage caused by improper use of the product. The values of specific weight, solids by volume and yields were calculated by theoretical methods. This sheet supersedes the previous editions.

---