



www.mondialcolor.it



COMPANY WITH  
CERTIFIED MANAGEMENT SYSTEM  
= UNI EN ISO 9001 =

## PRODUCT DATA SHEET

**PRODUCT:** **EPORUST TANK WR**  
**Very high solids water resistant coating**

**CODE:** **COMP. A 158 EPORUST TANK WR**  
**COMP. B 900013 - CAT. EPOX SPECIALE 13 WR**

**PRODUCT DESCRIPTION:** Anticorrosive coating with high solids and thickness, with white tars. It has high resistance to water, easy one-coat application. These features make it an ideal product for coating both exterior and interior of water tanks (not for food use), or in all cases a waterproofing is needed. It has excellent mechanical properties, impact resistance, abrasion, bending: it is resistant to lubricating oils, kerosene and naphtha too. EPORUST TANK WR can be used to isolate bridges/flow of latent currents in a system, thanks to the peculiar barrier effect, in order to reduce the electrocorrosion phenomenon.

**SURFACE PREPARATION:** On sandblasted surfaces apply to almost white metal (2½), perfectly free of oil, grease, dust, moisture or any other contaminant.

**APPLICATION METHODS:** Spray, brush or roll. Preferred application is airless spray. Brush or roller don't grant an uniform coverage, use these techniques only on retouch or small surfaces.

<b>APPLICATION INSTRUCTIONS:</b>	<b>CONVENTIONAL SPRAY LOW PRESSURE PUMP</b>		<b>AIRLESS AIRMIX</b>	
	Nozzle diameter (mm)	<b>na÷na</b>	Pressure ratio	<b>45:1</b>
Product pressure (Atm)	<b>na÷na</b>	Nozzle diameter (inch)	<b>0,015÷0,019</b>	
Air pressure	<b>na÷na</b>	Product pressure (Atm)	<b>170,0÷220,0</b>	



www.mondialcolor.it



COMPANY WITH  
CERTIFIED MANAGEMENT SYSTEM  
= UNI EN ISO 9001 =

## TECHNICAL DATA:

Mechanism of hardening	<b>Chemical reaction</b>
Specific weight (kg / l) *	<b>1,58 (±3%)</b>
Volume solids (%) *	<b>93 (±3%)</b>
Medium dry film thickness (microns)	<b>350-450</b>
Correspondence wet film thickness (microns)	<b>380-485</b>
Yield to the average or recommended thickness (m <sup>2</sup> / kg) *	<b>1,7-1,3</b>
Consumption at the average or recommended thickness (Kg / m <sup>2</sup> ) *	<b>0,6-0,8</b>
Touch dry at 25 ° C (min)	<b>120</b>
Recoat time min. recommended 25 ° C (hours)	<b>8</b>
Recoat time max. recommended 25 ° C (days)	<b>1</b>
Hard dry at 25 ° C (days)	<b>8</b>
Recommended application temperature (° C)	<b>+10 ~ +40</b>
Maximum operating temperature (° C)	<b>98</b>
Pot life at 25 ° (hours)	<b>2</b>
Mixing ratio by weight	<b>15%</b>
Thinner	<b>603.0000</b>
Aspect of the film	<b>matt</b>
Color	<b>White, black</b>
Storage in suitable conditions (months)	<b>12</b>

N.B.

\* Data referred to colour black. The solid content values, specific weight and yield were calculated with theoretical method. Thickness and performance are only indicative, in fact vary greatly depending condition of substrate, dilution, absorption, porosity, surface irregularities and application method. Data referred to the mixture of component A + 15% by weight of Comp.B



[www.mondialcolor.it](http://www.mondialcolor.it)



COMPANY WITH  
CERTIFIED MANAGEMENT SYSTEM  
= UNI EN ISO 9001 =

#### ADDITIONAL INFORMATION:

This is a two-component product. Before mixing the two components it is recommended to homogenize the component possibly with agitator and shake vigorously, possibly without opening, the packaging of component b. After mixing and addition of appropriate thinner, agitation should be continued until it became homogeneous. In order to use the correct mix ratio, necessary to obtain the best results, we recommend to catalyse only entire packs. In case you want to use only a portion of the pack, you should equip with adequate precision scale for catalysis by weight and appropriate sized containers for catalysis by volume. The pot life (time of use after catalysis) is significantly reduced by increase of temperature. Ambient temperature has influence on curing time which, under 10° C is extended considerably. Epoxy products are not suitable to use at low temperatures (typically under 5-8° C), except through the use of a specific catalyst (winter grade). The temperature of the surface to be treated must be at least 3° C higher than dew point. If this condition is not met the resulting condensation, not always visible, may easily lead to phenomena of non-adherence. The coating requires a period of 7-15 days at 25° C for complete curing. Carefully remove any accumulated roughness prior to the application of subsequent coats. It is recommended to implement all necessary measures (development of equipment for painting, using any thinner retardant-wetting thinner, position yourself upwind, proper progression of the surfaces to be painted) to prevent the accumulation of dust coating, which if not removed causes inhomogeneity of the film. The over-coating should be performed preferably within two days. After this time, to ensure a secure adhesion of additional coats is recommended to abrade with steel wool or fine sandpaper.

#### IMPORTANT NOTE

All information contained in this form are the result of laboratory tests carried out under controlled conditions and well-defined and / or correspond to our most advanced and current technical and practical knowledge. this does not exempt the customer, given the variability of environmental conditions and personal systems of application, from carrying out their own investigations and to make their own eligibility checks. Mondial Color assumes no responsibility for any damage caused by improper use of the product. This sheet supersedes the previous editions.