



www.mondialcolor.it



COMPANY WITH
CERTIFIED MANAGEMENT SYSTEM
= UNI EN ISO 9001 =

PRODUCT DATA SHEET

PRODUCT: **EPOPAINT 750**
Two-component high build epoxy-amine coating

CODE: **COMP. A 334 EPOPAINT 750**
COMP. B 9000075 - CAT EPOSSIDICO SPECIALE 75

PRODUCT DESCRIPTION:

Anticorrosive mastic with Surface Tolerant properties, self-priming, high solid content and high thickness. It has excellent adhesion to metals, galvanized steel, on old paint and on deteriorated surfaces. The product allows the achievement of any thickness without sagging, up to a maximum of 600 microns wet, smoothly covering edges and corners. These features make it an ideal product for the maintenance of damaged coatings where sandblasting is often not possible. EPOPAINT 750 is a durable primer-topcoat even on new surfaces, has excellent mechanical and chemical properties, impact resistance, abrasion, bending, resists against different chemicals including oils, kerosene, naphtha, both basic and acid solutions. EPOPAINT 750 can be used as primer, intermediate coat, topcoat or as single-coating. The product could be used in painting cycles when the specifications of the ISO 12944-5 standard are required, up to category C5-h.

SURFACE PREPARATION:

The better the preparation of the substrate, better and longer lasting will be the result. For particularly harsh operating conditions we recommend a white metal blasting (grade Sa3). For less severe conditions an almost white metal (grade Sa 2½) is enough. A commercial blasting or alternatively a good quality mechanical cleaning are often acceptable. Completely remove everything that is not tight and compact, such as rust, old paint, contamination from dirt, grease etc. The product must be applied strictly on dry surfaces, clean, perfectly free of oil, grease, dust, moisture or other contaminants.

APPLICATION METHODS:

Spray, brush or roll. Preferred application is airless spray. Brush or roller don't grant a uniform coverage, use these techniques only on retouch or small surfaces.

APPLICATION INSTRUCTIONS:

CONVENTIONAL SPRAY LOW PRESSURE PUMP		AIRLESS AIRMIX	
Nozzle diameter (mm)	--	Pressure ratio	45:1
Product pressure (Atm)	--	Nozzle diameter (inch)	0,017÷0,021
Air pressure	--	Product pressure (Atm)	180,0÷250,0



www.mondialcolor.it



COMPANY WITH
CERTIFIED MANAGEMENT SYSTEM
= UNI EN ISO 9001 =

TECHNICAL DATA:

	Chemical reaction
Mechanism of hardening	
Specific weight (kg / l) *	1,38 (±3%)
Volume solids (%) *	79,2 (±2%)
Medium dry film thickness (microns)	200
Correspondence wet film thickness (microns)	252
Yield to the average or recommended thickness (m ² / kg) *	2,9
Yield to the average or recommended thickness (m ² / lt) *	4
Touch dry at 25 ° C (min)	120
Recoat time min. recommended 25 ° C (hours)	6
Recoat time max. recommended 25 ° C (days)	5
Hard dry at 25 ° C (days)	6
Recommended application temperature (° C)	+10 ~ +40
Maximum operating temperature (° C)	120
Pot life at 25 ° (hours)	2
Mixing ratio by volume	16,5%
Mixing ratio by weight	11,0%
Thinner	603.0000 o 606.0001
Dilution (w/w %, for airless application)	5%Max
Aspect of the film	satin
Color	On request
Storage in suitable conditions (months)	12

N.B.

* Data referred to colour ral 5019. The solid content values, specific weight and yield were calculated with theoretical method. Thickness and performance are only indicative, in fact vary greatly depending condition of substrate, dilution, absorption, porosity, surface irregularities and application method. Data referred to the mixture of component A + 16,5% by volume of Comp.B



www.mondialcolor.it



COMPANY WITH
CERTIFIED MANAGEMENT SYSTEM
= UNI EN ISO 9001 =

ADDITIONAL INFORMATION:

This is a two-component product. Before mixing the two components it is recommended to homogenize the component possibly with agitator and shake vigorously, possibly without opening, the packaging of component b. After mixing and addition of appropriate thinner, agitation should be continued until it became homogeneous. In order to use the correct mix ratio, necessary to obtain the best results, we recommend to catalyse only entire packs. In case you want to use only a portion of the pack, you should equip with adequate precision scale for catalysis by weight and appropriate sized containers for catalysis by volume. The pot life (time of use after catalysis) is significantly reduced by increase of temperature. Ambient temperature has influence on curing time which, under 10° C is extended considerably. Epoxy products are not suitable to use at low temperatures (typically under 5-8° C), except through the use of a specific catalyst (winter grade). The temperature of the surface to be treated must be at least 3° C higher than dew point. If this condition is not met the resulting condensation, not always visible, may easily lead to phenomena of non-adherence. The coating requires a period of 7-15 days at 25° C for complete curing. The over-coating should be performed preferably within two days. After this time, to ensure a secure adhesion of additional coats is recommended to abrade with steel wool or fine sandpaper. As is widely known, the UV rays are able to cause the surface chalking of epoxy coatings causing an aesthetics alteration, which however does not compromise in any way the performance. Carefully remove any accumulated roughness prior to the application of subsequent coats. It is recommended to implement all necessary measures (development of equipment for painting, using any thinner retardant-wetting thinner, position yourself upwind, proper progression of the surfaces to be painted) to prevent the accumulation of dust coating, which if not removed causes inhomogeneity of the film. This product, when used as a primer can be recoated with acrylic, polyurethane and epoxy products.

IMPORTANT NOTE

All information contained in this form are the result of laboratory tests carried out under controlled conditions and well-defined and / or correspond to our most advanced and current technical and practical knowledge. this does not exempt the customer, given the variability of environmental conditions and personal systems of application, from carrying out their own investigations and to make their own eligibility checks. Mondial Color assumes no responsibility for any damage caused by improper use of the product. This sheet supersedes the previous editions.